



World's Strongest Bond™
www.jbweld.com



Technical Data Sheet

Revision date:
September 2020

ClearWeld™

PRODUCT BRIEF

ClearWeld™ is a quick setting, multipurpose two-part epoxy that provides a strong and lasting bond on most surfaces including tile, most plastics, ceramic, glass, wood and metal. ClearWeld™ is designed to cure with a clear, transparent bond when used at thicknesses of less than 15 mil. ClearWeld™ has a 1:1 mixing ratio, sets in 5 minutes and will fully cure within an hour. With a tensile strength of 3900 PSI, ClearWeld™ sets to a hard, permanent bond.

Part Number	Container Size		
50112	25mL Syringe		
50114	14mL Syringe		

PRODUCT BENEFITS

- Dries Clear
- Strength is 3900 PSI
- Sets in 5 minutes
- Includes stir stick and mixing tray
- Allows for precise 1 to 1 mix

TYPICAL APPLICATIONS

- Use on Metal/Plastic*/Wood/Concrete/Ceramic Tile/Fiberglass
- Home/Auto/Toy/Plumbing/Industrial/and Marine Repairs
- Crafts and Outdoor Equipment



DIRECTIONS FOR USE

1. **PREPARE SURFACE:** Clean repair area of dirt, grease, oil, paint, rust, etc. For best results use a detergent or degreaser to clean the surface, then roughen surface with file or coarse sandpaper to provide the best repair.
2. **MIX:** After removing the replaceable cap, press down on plunger and squeeze equal amounts onto a disposable surface and mix thoroughly.
3. **APPLICATION:** Apply with appropriate tool in an even coat, weld bead or extrude shape as needed.
4. **DRYING:** Sets in 5 minutes. Cures in 1 hour. If temperature is below 40°F, then set time is longer.

VOC Status:

Compliant for sale in all 50 States.

DISCLAIMER

**Not recommended for Polyethylene Plastic (PE), Polypropylene Plastic (PPE), Nylon, and other highly flexible materials and non-porous surfaces.*

The information and recommendations contained herein are based on our research and are believed to be accurate, but no warranty, express or implied, is made or should be inferred. Purchasers should test the products to determine acceptable quality and suitability for their own intended use.